

3F, Building Block 2, No. 3400 Gonghexin Road,
Jing'an District - Shanghai 200436, P.R. CHINA
上海市静安区共和新路3400号2幢3层
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

TEST REPORT

Page 1/3

Report No.: S230402668_1

06 April 2023

hr-sh@jdlisafety.com
ronnie.gu@jdlisafety.com

APPLICANT: NANTONG JIADELI SAFETY PRODUCTS CO.
LTD 南通嘉得利 (C00498)
SHUANGDIAN INDUSTRIAL PARK C RUDONG
226400 RUDONG JIANGSU
CHINA

Date of receipt : 03 Apr. 2023
Testing period : 06 Apr. 2023
: 06 Apr. 2023

Buyer: ---

Sample description: 21 gauge grey cut resistant shell with black palm dipped PU coating glove

Style / Article no. : PD6870
Test(s) requested : ---
Service : REGULAR
Brand / Section : ---
Season : ---
End use : ---
Factory name : ---
Factory code : ---

For CE Marking : Yes

Previous report : ---
Product category : ---
Product type : ---
Test stage : FIRST TEST
Supplier name : ---
Exported to : ---

1. Conclusion:

	Tests description	Conformity
	ANSI-ISEA 105: 2016	
1	Cutting resistance TDM	Level A6

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN 严滨
Laboratory Manager



TEST REPORT

Report No.: S230402668_1

06 April 2023

APPLICANT: NANTONG JIADELI SAFETY PRODUCTS CO.
LTD 南通嘉得利 (C00498)

2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
	GLOVE	palm	



230402668

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.

The report is for internal reference only and not for social proof use.



TEST REPORT

Report No.: S230402668_1

06 April 2023

APPLICANT: NANTONG JIADELI SAFETY PRODUCTS CO.
LTD 南通嘉得利 (C00498)

3. GLOVE/

palm

	Method	Client Requirement	Unit	Result	Conformity
(+) 5.1.1. Cutting resistance TDM Correction factor of the sharp edge of the blade with the neoprene Load for a distance of 20 mm cut Performance level	ASTM F2992 /F2992M - 15		g	0.83 3500 Level A6	

END OF TEST REPORT

(+)CNAS accreditation

Unless otherwise specified, the physical test items in this report performed in CTC Shanghai lab were conditioned and tested in the environment of T 23±2°C / RH 50±4%.

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard

Classification Table for Cut Resistance (ANSI-ISEA 105)

Level	Weight (grams) needed to cut through material with 20 mm of blade travel
A1	>=200
A2	>=500
A3	>=1000
A4	>=1500
A5	>=2200
A6	>=3000
A7	>=4000
A8	>=5000
A9	>=6000

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.

The report is for internal reference only and not for social proof use.

